

Product Bulletin

supresta™
BUILT-IN DEFENSE

Phosflex® 390


Phosflex®
Flame Retardant Plasticizers

Chemical Name: Isodecyl diphenyl phosphate

CAS

Isodecyl diphenyl phosphate 29761-21-5

Triphenyl phosphate 115-86-6



Phosflex® Product Selector

	Key applications	Key characteristics
4	<ul style="list-style-type: none">• Primary plasticizer for nitro-cellulose, chlorinated rubber• Anti-foam agent	<ul style="list-style-type: none">• Low viscosity• Low density
31L	<ul style="list-style-type: none">• PVC film and sheet compounds• Dispersant for plastisols	<ul style="list-style-type: none">• Low color• Blendable with non-FR plasticizers
41L	<ul style="list-style-type: none">• PVC film and sheet compounds• Dispersant for plastisols	<ul style="list-style-type: none">• Low color• Blendable with non-FR plasticizers
71B	<ul style="list-style-type: none">• Flame retardant plasticizer for PVC	<ul style="list-style-type: none">• Excellent flame retardant properties• Low volatility
362	<ul style="list-style-type: none">• Flame retardant plasticizer for PVC alloys	<ul style="list-style-type: none">• Low temperature and low smoke• Excellent vinyl solvating properties• Approved for packaging materials in food contact
390	<ul style="list-style-type: none">• Flame retardant plasticizer for PVC sheets and coatings	<ul style="list-style-type: none">• Excellent low temperature flexibility• Low smoke, good weathering properties
314, 318, 321, 327	<ul style="list-style-type: none">• Blended plasticizer for film and sheet vinyl goods	<ul style="list-style-type: none">• High efficiency• High solvating

Overview

Phosflex® 390 is isodecyl diphenyl phosphate made from synthetic feedstocks. It is a highly efficient plasticizer for PVC, with very good low temperature flexibility, and excellent solvating properties for fast fusion.

One of the unique characteristics of Phosflex® 390 is its ability to reduce flammability while also reducing smoke. Typically when flame retardants are used, the combustion efficiency of the compound is decreased and as a result, smoke (incomplete combustion particles and gases) increase. Phosflex® 390 does both exceeding well in many types of polymer systems, especially flexible vinyl and vinyl alloys.

Phosflex® 390 has excellent compatibility in PVC and other plastics. Formulated correctly, this product performs well in vinyl composites for outdoor applications where exposure to UV irradiation and weathering is critical. Phosflex® 390 has been found useful in FR foamed vinyl and vinyl alloys (PVC/nitrile rubber), calendared sheet goods, vinyl wire and cable and outdoor PVC applications. In certain elastomers, Phosflex® 390 can be useful as a solvator to improve the tactile feel of the rubber composites.

Key Applications

Formulations for Flexible Suspension PVC at 50 phr Plasticizer

	1	2	3	4	5
PVC Geon (103EP)	100	100	100	100	100
CaCO ₃	50	50	50	50	50
Zinc Borate (Firebrake ZB)		3	6	3	6
ATH (Hydral 710)				20	40
Plasticizers	50	50	50	50	50
ESO (Plastoflex 2307)	5	5	5	5	5
Stabilizers (Ba/Zn mixed metals)	5	5	5	5	5
Totals (parts)	210	213	216	233	256

These five formulations represent basic formulation and component variations typically seen for FR-PVC. The resultant flammability and physical properties are shown in the following tables with comparisons to similar flame retarded vinyl systems.

Phosflex® 390 in PVC Suspension Resin (GEON 103GP)

Component	Additive phr	Tensile Properties			Hardness		LOI 100 Mils	UL-94 1.6mm
		Strength psi (MPa)	E Mod. psi (MPa)	Elong. %	Shore "A" Initial	Creep (15 sec.)		
DIDP	50	1844(12.7)	858(5.9)	426	88	85	23	FAIL
ZB	3	2018(13.9)	907(6.2)	461	88	84	23.2	FAIL
ZB	6	1824(12.6)	906(6.2)	417	90	86	23.2	FAIL
ZB/ATH	3/20	1635(11.3)	945(6.5)	359	91	86	23.6	FAIL
ZB/ATH	6/40	1715(11.8)	1081(7.4)	374	93	89	25	FAIL
Phosflex® 390	50	1608(11.1)	752(5.2)	373	86	83	27.2	V-0
ZB	3	1320(9.1)	756(5.2)	291	88	84	27.8	V-0
ZB	6	1510(10.4)	777(5.4)	352	90	86	28	V-0
ZB/ATH	3/20	1535(10.6)	863(5.9)	364	91	86	28.2	V-0
ZB/ATH	6/40	1460(10.1)	995(6.9)	336	93	89	29.6	V-0

Typical Properties

Physical appearance	Clear, transparent liquid
Phosphorus content, wt. %	7.9
Specific gravity, 20°C/20°C	1.070
Density @ 20°C, lbs/gal	8.9
kg/m ³	1070
Viscosity @ 25°C, mPa.s	26
Acidity, as phosphoric acid, %	0.10
Water content, wt. %	0.10
Color, APHA	<100


Safety & Handling

Consult the Material Safety Data Sheet for this product.

Shipping Information

Available in bulk tank trucks, isocontainers, 2,300 lb totes, and 480 lb drums.

Thermogravimetric Analysis: Phosflex® 390 (10°C rise/minute in nitrogen)



2% wt. Loss	204°C
5% wt. Loss	221°C
10% wt. Loss	234°C

For more information about our products and to place an order, please contact one of Supresta's regional sales offices.

AMERICAS REGIONAL SALES OFFICE
Ardsley Park at 420 Saw Mill River Road
Ardsley, New York 10502 USA
914.269.5900, 800.666.1200
fax 914.674.9735

ASIA PACIFIC REGIONAL SALES OFFICE
12/B, Sun Tong Plaza, No.55 Huai Hai Road West
Shanghai 200030 China
86 21 5298 9058
fax 86 21 5298 9352

EUROPEAN REGIONAL SALES OFFICE
Hoefseweg 1, PO Box 2501
3800 GB Amersfoort, The Netherlands
31 33 4534 575
fax 31 33 4534578

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable as of the date of publication. However, no warranty is made as to the accuracy of and/or sufficiency of such information and/or suggestions as to the merchantability or fitness of the product for any particular purpose, or that any suggested use will not infringe any patent. Nothing herein shall be construed as granting or extending any license under any patent. Buyer must determine for itself, by preliminary tests or otherwise, the suitability of this product for its purposes, including mixing this product with other products. The information contained herein supersedes all previously issued bulletins on the subject matter covered.